

Granosil'plus STF

Primer coat for silicone renders

Field of Application

Ideal primer for all silicone resin bonded renders outside.

Characteristic

Water vapour permeant, non swelling, low stress, non film forming, environmentally friendly.

Composition

Quartz-containing silicone resin bonded primer with special adherence additives.

Colours

The colour of the primer coat gransil'plus STF is matched to the colour of the top coat render.

There is an extensive choice of colour tones available. See our original samples. Special colour tones can be made on request. It is not possible to use colour tones with brightness references below 20.

Colour tone differences on the processed surface to the corresponding trials and treatments cannot be avoided because of the weather influenced drying processes. In the event of subsequent deliveries the remaining part of the material must be mixed with the new material on a continuity basis, to guarantee the same colour.

Preparation substrate

Substrates must be flat, load bearing, clean and dry. Loose parts should be removed or leveled out if necessary.

Do not use on substrates that are coated with plastic or shiny dispersion materials!

The directions of DIN 18363, the VOB, part C as well as the BFS-instruction sheets of the affected areas to be processed in the latest revision are to be regarded.

With dubious substrates please ask for our consulting services.

Application

With paint brush, brush or lamb skin roller, depending on substrate. Granosil'plus STF can be diluted with up to 10% water, depending on the substrate. Stir properly before use. The fresh Granosil'plus STF must be protected against torrential rain and too fast drying. Especially with direct sunlight and wind influence suitable countermeasures must be taken, such as e.g. covering of the façade or of the scaffold.

Do not apply when the substrate or the environmental temperatures are below 5° C.

Tools and equipment must be cleaned with water immediately after use. Surrounding building parts, such as windows, window-sills etc. must be properly covered.

Coverage

0,2 – 0,3 kg/m² per coat with even substrates.

For an exact calculation the coverage must be determined by applying a test coat onto the object.



Granosil'plus STF

Primer coat for silicone renders

Technical data

Density:	1,79 kg/dm ³
----------	-------------------------

Packaging

Ready for processing in 12 / 18 / 25-kg containers.

Store in a cool and frost-free area. Protect against direct sunlight. Can be stored in a closed container for at least 1 year. Broached containers must be processed within a short period of time.

Special references

Surfaces that should not be treated, must be covered when spraying. Do not mix binders and additives.

Processing should be carried out according to the safety directions. All safety-related data can be found in the safety data sheets.

Disposal

Only emptied containers can be returned for recycling. Waste material must be dried before disposal according to key nr. 91206 (building waste).

Classification

EU VOC limit value for this product (cat A /c WB): 30 g / L

This product contains a maximum of 30 g / L VOC