Strasser'plus Refuga

Batching concentrate for Strasser Pflasterfuge



Field of Application

The pavement surface must be sprinkled lightly before and during the jointing. It can safely be used for the describred sector including the food and drinking water sector.

Characteristic

Strasser Refuga is used in the jointing of natural pavement, concrete slabs, cobblestone materials etc., as a surface retarder and prevents a too fast burning out of the jointing materials on the stone surface.

Composition

Strasser Refuga is a highly concentrated liquid harder stop based on an organic acid.

Preparation underground

Clean the joint area of the pavement with compressed air or with a high-pressure sprayer. Moisten joint area before applying joint material.

Application

Preliminary treatment of the surface:

The stone surface must be lightly sprayed with Strasser Refuga (mix 1 litre of Strasser Refuga batching concentrate with 9 litres of water). (e.g. with a Gloria garden spray).

For the processing metal containers or metal equipment should not be used.

Applying of the plaster grout:

Pour the mixed pavement grout onto the with Strasser Refuga presprayed pavement surface and spread it immediately with a squeegee. The best way to smooth the surface is to use a squeegee.

Important notice:

Strasser Refuga batching concentrate should only be used diluted with water. Be careful with limestone (e.g. marble etc.) When used with metal, rinse immediately with water and subsequently apply a corrosion protection (e.g. grease). Strasser Refuga is environmentally friendly and biodegradable.

Consumption

1 litre of Strasser Refuga batching concentrate (for approx. 6-15 m²)

Strasser'plus Refuga





Technical data

Colour:	clear
Base:	organic acids
Mixing ratio:	Strasser Refuga batching concentrate 1:9 mix with water
Processing temperature:	+5°C to +25°C surface temperature

Packaging

- 1 year, frost-free in a closed container.
- 1 liter plastic bottle

Special references

Because Strasser Refuga batching concentrate is a corroding and cauterizing agent, it shall only be handled and processed wearing rubber gloves and glasses. In the event of a brief skin contact immediately wash thoroughly with water and soap. In the event of eye contact thoroughly rinse with water immediately and consult a physician. Further informations can be found in our safety data sheets. (classified according to GefStoffV)

Cleaning of sett paving

As soon as the joint has been hardened (test by finger press, ca. 1-2 hours), the surface can be cleaned with a water hose and a sharp broom or with a high-pressure sprayer. The from the cleaning resulting mortar remnants must be neutralized with an abundance of water. Apply a sand trap!

When properly processed with Strasser Refuga the surface remains clean and the original nature of the stones will be kept.

Surface treating

Spray the pavement surface several times after applying the Strasser Pflasterfuge with Strasser Refuga, so the stone surface will not dry. In the event of wind, direct sunlight and strong heat, special attention should be paid that the surface has to be sprayed and kept wet with Strasser Refuga regularly during the hardening phase of the Pflasterfuge.